

**Specifications of Polyvinyl Alcohol**

Grades	Hydrolysis (mol%)	Volatiles (%)	Viscosity (mpa.s)	Ash (wt%)	PH Value	Purity (wt%)
Grades are being produced regularly						
PVA1788	87.0-89.0	≤5	20.5-24.5	≤0.4	5-7	≥93.5
PVA1895	94.0-96.0	≤5	26.0-30.0	≤0.5	5	≥93.5
PVA1799	98.0-99.4	≤5	23.0-29.0	≤0.7	5	≥93.0
PVA2488	87.0-89.0	≤5	45.0-55.0	≤0.5	5	≥93.5
Grades to be produced depending on time						
PVA0499	98.0-99.4	≤5	4.0-5.0	≤0.7	5	≥93.0
PVA0498	98.0-98.8	≤5	4.0-5.0	≤0.7	5	≥93.0
PVA0588	87.0-89.0	≤5	4.5-6.0	≤0.7	5	≥93.0
PVA0599	98.0-99.0	≤5	5.0-6.5	≤0.7	5	≥93.0
PVA1098	97.0-99.0	≤5	8.0-12.0	≤0.5	5	≥93.5
PVA1399	98.0-99.0	≤5	13.0-17.0	≤0.5	5	≥93.5
PVA1797	96.0-98.0	≤5	23.0-29.0	≤0.7	5	≥93.5
PVA2088	87.0-89.0	≤5	29.0-34.0	≤0.5	5	≥93.5
PVA2497	96.0-98.0	≤5	54.0-64.0	≤0.5	5	≥93.5
PVA2499	98.0-99.0	≤5	55.0-65.0	≤0.5	5	≥93.5
Grades can be produced						
PVA1897	96.0-98.0	≤5	27.0-31.0	≤0.5	5	≥93.5
PVA1795	94.0-96.0	≤5	22.0-28.0	≤0.5	5	≥93.5
PVA1899	98.0-99.0	≤5	28.0-32.0	≤0.5	5	≥93.5
PVA2099	98.0-99.0	≤5	34.0-39.0	≤0.5	5	≥93.5
PVA2288	87.0-89.0	≤5	38.0-42.0	≤0.5	5	≥93.5
PVA1792	91.0-93.0	≤5	21.0-27.0	≤0.5	5	≥93.5
PVA2092	91.0-93.0	≤5	28.0-34.0	≤0.5	5	≥93.5