



1050 Industry Boulevard, Saint-Jérôme, Québec, Canada, J7Y 4B9
(800) 561-6511, (450) 240-5550, www.stobec.com

PRODUCT SPECIFICATION

Tetramethyl Thiuram Monosulfide (TMTM)

Properties	Limits
Appearance	Yellow Powder
Assay %	96.0 min
Ash	0.30 max
Density at 20°C (kg/m ³)	1400
Melting Point (Initial), C	103 min
Heat Loss (70°C x 2hrs), %	0.30 max
Residue on Sieve (63 µm)	0.50 max
Residue on Sieve (150 µm)	0.10 max
Oil Content, %	1.0-2.0

This analysis is furnished without warranty, representation, inducement or license of any kind, except that it is accurate to the best of STOBEC's knowledge, or obtained by sources believed by STOBEC to be accurate. STOBEC do not assume any legal responsibility for use or reliance upon same. Tests should be carried out only by chemists or chemically qualified lab technician. Before using any chemical, read its label and Material Safety Data Sheet.