

ADGEL® SDSF-810

ADGEL SDSF-810 is a modified Guar gum specially developed and recommended for construction applications. It improves the performance when typically applied in Cement based wall putty, Cement-Gypsum based plasters, Cement-Gypsum based crack fillers, Cement based texture plasters, flooring and leveling compounds.

Basic Technical data:

Constitution	Modified Guar Gum
Appearance of the powder	Free flowing Creamish powder
Ionic Nature	Non-ionic
pH of 10 % solution	6.5 -7.5
Moisture	≤ 10 %
Viscosity* of 10 % solution	8,000 – 12,000 cps

Viscosity*: Viscosity of the Std. solution is measured by Brookfield Viscometer, model RVF, with spindle no. 6,20 rpm @ 25°C.

Applications: ADGEL SDSF-810 gives best consistency and water retention property for construction applications. It allows the mixture to maintain the water level inside final mixture that improves the open time in different construction quality mixtures. **ADGEL SDSF-810** can also be used in combination of Cellulose ethers products.

Preparation Method: ADGEL SDSF-810 is cold water soluble and easily converted in to transparent paste form in short period of time. In a well cleaned container, take 90 liters of soft water and add 10 kg ADGEL SDSF-810 powder during stirring condition. Mix it well till to form a uniform paste solution. **ADGEL SDSF-810** powder can also be used directly in dry mixture formulations with suitable dosages.

Advantages:

Easily soluble in cold water, Better Rheological properties, Enhance the workability in Gypsum based dry mixtures, Improve the adhesion strength and open time in final mixtures, work as better anti-sagging and easy applications, Cost effective formulations., Eco-friendly.

Compatibility: Compatible with most of the chemicals normally used in construction chemicals. It is not advisable to mix the product with gum Arabic and Crystal gum. It coagulates with borate and tannin.

Shelf Life: 12 months.

Packing: 25.0 kg white/brown paper bag with one PE liner inside.

Note: Above information is best of our knowledge and can be used for guideline only. Customer need to test their own and accordingly to their suitability, use and processing. We take no guarantee or warrantee for any loss caused by use, handling or processing of our product.

Factory Address: C1, 91/14, GIDC Estate, Phase-1, Vatva, Ahmedabad-382 445 Gujarat- India. Tel: +91-79-2583 1375-76, Fax: +91-79-2589 3255. Email: info@adachigroup.com, Web: www.adachigroup.com